

# Linear Low Density Polyethylene



## LF20186

EVALENE<sup>®</sup> LF20186 is a high slip, high antiblock Linear Low Density Polyethylene grade with butene (C4) as comonomer for blown film applications.

**EVALENE<sup>®</sup> LF20186** is tailored for thin to medium thickness films (25 to 50 microns; 0.001" to 0.002"). It is especially designed to work well when blended with low density polyethylene (LDPE). It is likewise suitable as lamination layer or core layer material in coextruded films. Films made with **EVALENE<sup>®</sup> LF20186** are notable for their toughness, flexibility and clarity - a good combination of mechanical and optical properties.

### FEATURES

- Outstanding mechanical properties
- Excellent compatibility for blending with LDPE
- Enhanced clarity
- Meets FDA Philippines food-contact requirements
- Halal certified

### TYPICAL APPLICATIONS

- Flexible packaging
- Agricultural films
- Industrial liners
- Garment bags
- Trash bags
- Shopping bags
- Ice bags

## Product Properties

Property	Test Condition	Test Method	Typical Value	Unit
Melt Index	190°C/2.16 kg	ASTM D1238	2.0	g/10 min
Density	23°C	ASTM D1505	0.918	g/cm <sup>3</sup>
Tensile Strength at Yield*	500 mm/min	ASTM D882	9 / 9	MPa
Elongation at Yield*	500 mm/min	ASTM D882	57 / 30	%
Tensile Strength at Break*	500 mm/min	ASTM D882	12 / 11	MPa
Elongation at Break*	500 mm/min	ASTM D882	478 / 444	%
Tensile Modulus*	1% Secant, 25 mm/min	ASTM D882	160 / 178	MPa
Elmendorf Tear Strength*		ASTM D1922	213 / 399	g
Dart Drop Impact Strength*		ASTM D1709	64	g
% Haze*		ASTM D1003	11	%
Gloss*	45° angle of incidence	ASTM D2457	80	%
Coefficient of Friction - Static*		ASTM D1894	0.16	-
Coefficient of Friction - Kinetic*		ASTM D1894	0.12	-

\*Properties tested on 25µ films made using a Killion extruder with 38mm screw, 3.5" die, 1.0mm die gap, at 2.25:1 BUR. Tensile and tear properties are in machine and transverse directions (MD / TD).

### Typical Processing Conditions

Extrusion Temperatures	170 - 190°C
Blow Up Ratio	2 - 4
Die Gap	1 - 3 mm

**EVALENE® LF20186** has balanced mechanical properties overall. It has comparable tensile, tear and dart properties with the 2.2 MI, 923 Density LLDPE material.




Figure 1. Mechanical property performance of **EVALENE® LF20186** vs. a 2.2 MI, 923 Density LLDPE material




Figure 2. Comparison of haze between **EVALENE® LF20186** and 2.2 MI, 923 Density LLDPE material




Figure 3. Comparison of gloss between **EVALENE® LF20186** and 2.2 MI, 923 Density LLDPE material

When it comes to clarity, **EVALENE® LF20186** stands out. It has almost 30% lower haze and more than double gloss compared to the other LLDPE material. Such outstanding optical properties allow **EVALENE® LF20186** to deliver stunning optics that both the films producer and the end-user want.

**Disclaimer:**

Information provided herein is given for general purposes only. It is the customer's sole responsibility to test the product and any information provided herein to determine whether they are suitable for the customer's purposes. JGSPC MAKES NO REPRESENTATIONS OR WARRANTIES, EITHER EXPRESS OR IMPLIED, OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE OR OF ANY OTHER NATURE ARE MADE HEREUNDER WITH RESPECT TO INFORMATION OR THE PRODUCT TO WHICH INFORMATION REFERS. Customers are strongly advised to review the applicable Material Safety Data Sheet before handling or using the product described herein.



Find out more about us at:  
[www.jgspetrochem.com](http://www.jgspetrochem.com)



Better Life Through Innovation