

Homopolymer Polypropylene

PHF0702

EVALENE[®] PHF0702 is a high slip, high antiblock Homopolymer Polypropylene grade for tubular water quench film applications (also referred to as iPP).



EVALENE[®] PHF0702 is the recommended grade for iPP in the thickness range of 8 to 15 microns (0.0003" to 0.0006"). Thin iPP made of **EVALENE[®] PHF0702** has excellent clarity and transparency, delivering outstanding shelf appeal and numerous promotion opportunities. **EVALENE[®] PHF0702** films are easy to open, allowing faster processing during packaging. They also exhibit exceptional toughness making downgauging a real possibility.

FEATURES

- Outstanding optical properties
- Excellent openability
- Superior toughness
- Good organoleptic properties
- Meets FDA Philippines food-contact requirements
- Halal certified

TYPICAL APPLICATIONS

- Thin films, from 8 to 15 microns (0.0003" to 0.0006"), for food and general packaging

Product Properties

Property	Test Condition	Test Method	Metric Value	Unit
Melt Flow	230°C/2.16 kg	ASTM D1238	7	g/10 min
Tensile Strength at Yield*	500 mm/min	ASTM D882	23 / 20	MPa
Elongation at Yield*	500 mm/min	ASTM D882	23 / 8	%
Tensile Strength at Break*	500 mm/min	ASTM D882	46 / 11	MPa
Elongation at Break*	500 mm/min	ASTM D882	359 / 287	%
Tensile Modulus*	1% Secant, 25 mm/min	ASTM D882	663 / 710	MPa
Elmendorf Tear Strength*		ASTM D1922	57 / 466	g
% Haze*		ASTM D1003	1.12	%
Gloss*	60° angle of incidence	ASTM D2457	123	%
Coefficient of Friction - Static*		ASTM D1894	0.15	-
Coefficient of Friction - Kinetic*		ASTM D1894	0.10	-

*Properties tested on 10µ film.

Tensile and tear properties are in machine and transverse directions (MD / TD).

Properties based on ASTM Type I injection molded samples available upon request.

Typical Processing Conditions

Extrusion Temperatures
Chill Roll/Water Bath

185 - 220°C
23 - 30°C

This side-by-side comparison clearly highlights that **EVALENE® PHF0702** is superior to the other iPP material in mechanical properties. In both toughness and strength, **EVALENE® PHF0702** delivers performance that exceeds the film producer's requirements and meets the end-user's expectations. The combination of outstanding tensile, tear and dart drop impact strengths of **EVALENE® PHF0702** guarantees that the film is strong enough even just at 8 to 15 microns.




Figure 1. Mechanical property performance of **EVALENE® PHF0702** vs. other iPP material




Figure 2. Comparison of haze between **EVALENE® PHF0702** and other iPP material (10 micron film)




Figure 3. Comparison of gloss between **EVALENE® PHF0702** and other iPP material (10 micron film)




Figure 4. Blocking force of **EVALENE® PHF0702** (10 micron film)

EVALENE® PHF0702 is the market leader due to its superior clarity. It has 4x less haze than the other iPP material, a feat that **EVALENE®** continuously delivers, resulting in clarity that has become the standard in the iPP market.

EVALENE® PHF0702 has low blocking force that gives excellent film openness.

Disclaimer:

Information provided herein is given for general purposes only. It is the customer's sole responsibility to test the product and any information provided herein to determine whether they are suitable for the customer's purposes. JGSPC MAKES NO REPRESENTATIONS OR WARRANTIES, EITHER EXPRESS OR IMPLIED, OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE OR OF ANY OTHER NATURE ARE MADE HEREUNDER WITH RESPECT TO INFORMATION OR THE PRODUCT TO WHICH INFORMATION REFERS. Customers are strongly advised to review the applicable Material Safety Data Sheet before handling or using the product described herein.

only. It is the customer's sole responsibility to test the product and any information provided herein to determine whether they are suitable for the customer's purposes. JGSPC MAKES NO REPRESENTATIONS OR WARRANTIES, EITHER EXPRESS OR IMPLIED, OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE OR OF ANY OTHER NATURE ARE MADE HEREUNDER WITH RESPECT TO INFORMATION OR THE PRODUCT TO WHICH INFORMATION REFERS. Customers are strongly advised to review the applicable Material Safety Data Sheet before handling or using the product described herein.



Find out more about us at:
www.jgspetrochem.com



Better Life Through Innovation